



## ENGINEERING & TECHNICAL DATA — Flexadux® TR LCDC

INSIDE DIAMETER (IN)	APPROX. WEIGHT (LBS/FT)	WALL THICKNESS (IN)	CL BEND RADIUS (IN)	COMPRESSION RATIO	NEGATIVE PRESSURE (IN/HG)	WORKING PRESSURE (PSI)
6	1.2	.032	5.25	2:1	12	10
8	1.5	.032	7.5	2:1	11	8
10	1.9	.032	8	3:1	9	4
12	2.2	.032	10	3:1	7	2.5

Technical data based on 2 ft. straight lengths of hose @ 72°

**Construction:** Medium weight high performance polypropylene blend hose reinforced with a spring steel wire helix & external polypropylene wearstrip

**Temperature Range:** -30°F to 200°F

**Standard Color:** Black with Orange Wearstrip

**Standard Lengths:** 25 Feet

Disclaimer: The proper use and maintenance of hose and/or ducting manufactured by Flexaust is the sole responsibility of the purchaser and ultimate user of the product. This information is presented as a general guide only. The number of variables which can be present in any application make firm recommendations impossible.

Tel: 574-267-7909 • Toll Free Tel: 800-343-0428 • Toll Free Fax: 800-382-8464  
sales@flexaust.com • www.flexaust.com



A SCHAUBENBURG HOSE TECHNOLOGY COMPANY